



2010 Recycled Steel Content for All Products by Mill

Mill	Post-consumer Scrap Content %	Pre-consumer Scrap Content %	Home or revert Scrap %	Total Recycled Content %	Non Recycled Content %	*Products Produced
Beaumont, TX	73.4	9.0	7.0	89.3	10.7	W
Beaumont, TX	81.3	9.9	7.7	99.0	1.0	R
Calvert City, KY	83.8	11.6	3.0	98.4	1.6	M, S
Cambridge, Ontario	74.2	19.2	5.3	98.8	1.2	M, R
Cartersville, GA	79.4	16.4	2.1	97.9	2.1	M, S
Charlotte, NC	88.0	5.5	5.5	98.9	1.1	M, R
Jackson, TN	88.1	7.3	3.5	98.9	1.1	M, S
Jacksonville, FL	85.2	6.1	6.3	97.6	2.4	R, W
Joliet, IL	84.4	6.1	7.9	98.4	1.6	SBQ
Knoxville, TN	87.3	8.2	3.4	98.9	1.1	R
Selkirk, Manitoba	89.1	3.9	5.5	98.6	1.4	M, R, SBQ
Midlothian, TX	89.1	1.3	8.6	99.0	1.0	M, R, SBQ, S
Petersburg, VA	88.0	0.9	10.1	99.0	1.0	S
Rancho Cucamonga, CA (Tamco)	82.0	13.0	4.0	99.0	1.0	R
Sayreville, NJ	91.6	4.7	2.6	98.9	1.1	R
St Paul, MN	85.6	5.2	8.3	99.0	1.0	M, R, SBQ
Whitby, Ontario	92.1	6.9	0.0	99.0	1.0	M, R, S
Wilton, IA	84.7	5.5	7.9	98.1	1.9	M, R
All Mills	84.3	7.2	6.8	98.3	1.7	

Product Abbreviations: Merchant (M), Rebar (R), Special Bar Quality (SBQ), Structural (S), Wire Rod (W)